

SSP-502F-50
Conductive Fluorosilicone Elastomer

PRODUCT DESCRIPTION

The SSP502F-50 is a 50 durometer nickel coated graphite filled fluorosilicone elastomer. This product is supplied as ready-to-mold compound; fully cured, conductive sheet stock; continuous extrusion profiles; or, for some formulations, continuous rolls. The data below was generated using ASTM test methods and procedures.

DATA	Typical Values
Shore A (45- 55 range)	51
Tensile psi (100 minimum)	130 psi
Elongation % (200 minimum)	477%
Tear "B" ppi (25 min)	33
Specific Gravity (Report)	2.13
Volume Resistivity ohm / cm (0.1 max)	.015 ohm /cm
Color	Dark Gray
Thermal Stability Range	-55°C - 200°C
Shielding Effectiveness 100MHz-10GHz (E-Field)	> 113 dB

CATALYZING

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

SHELF LIFE

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

HANDLING & SAFETY

MSDS information is available on request.

For more information visit www.sspinc.com. To order call **(518) 885-8826/** or Fax **(518) 885-4682**.

Specialty Silicone Products, Inc.

Corporate Technology Park * 3 McCrea Hill Road * Ballston Spa, NY 12020

Specialty Silicone Products, Inc is an ISO 9001:2008 registered company.

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.