



SSP-1219

FDA COMPLIANT H1 SILICONE LUBRICATING COMPOUND

PRODUCT DESCRIPTION

SSP-1219 is a stiff, tacky lubricating compound designed for a wide range of applications where contacting surfaces are not under heavy load, but high temperatures are expected. SSP-1219 is useful as an electrical insulator, corrosion inhibitor, water repellent, mold release, and metal, rubber and plastic parts lubricant. SSP-1219 features no separation at temperatures up to 500°F, low volatility, non corrosive, plus ensures performance consistency and stability. SSP-1219 can be used in applications where indirect food contact can occur.

| DATA | TYPICAL VALUES |
|---|-----------------|
| Appearance | Translucent |
| Temperature | -100°F to 500°F |
| Worked Penetration (230 - 270 Range) | 255 |
| Unworked Penetration (200-250 Range) | 230 |
| Bleed (After 24 hours @ 200°C) | 0 % |
| Evaporation (After 24 hours @ 200°C) | 1.0 % |
| Specific Gravity (0.99 – 1.03) | 1.01 |

| FEATURES | APPLICATIONS | CONTAINERS |
|--|--|--|
| FDA Compliance 21CFR 178.3570 Low Volatiles Excellent Dispersion Wide Temperature Range Non Corrosive Excellent Stability Does Not Separate | Indirect Food Contact Fire Extinguisher Valves Vacuum / Pressure Systems Auto Ignition Plug Valves Electrical Connections Corrosion Protection | 400 lb. drum 40 lb. plastic pail 8 lb. Plastic Pail 1 lb. Jar 14.1 oz. Cartridge 5.3 oz. Tube |

Private labeling & specialty packaging are always available to meet customers' total requirements.

HANDLING & SAFETY

MSDS information is available on request.

For more information visit www.sspinc.com. To order call (518) 885-8826/ or Fax (518) 885-4682.

Specialty Silicone Products, Inc.

Corporate Technology Park * 3 McCrea Hill Road * Ballston Spa, NY 12020

Specialty Silicone Products, Inc is an ISO 9001:2008 registered company.

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.